

Unit 3 Cockerell Close  
Gunnels Wood Road  
Stevenage  
Hertfordshire  
SG1 2NB  
T: +44(0) 1438 777 700  
info@fira-international.com  
www.fira-international.com

**Allsave Textiles Ltd**

Unit 18  
Stafford Park 12  
Telford  
TF3 3BJ

Our Ref: **FL-61992-S2A\***

Date: 04 July 2023

Delivery Date: 21 June 2023

Test Dates: 21 June - 03 July 2023

For the attention of Sarah Clarke

**SAMPLE(S) FOR TEST:**

One, Non-Visible Fabric – Ref: Black Loop Pile Velcrotex Velour 100% Sandstone Black Granite White Brown Batch 148-149

*Note: The above descriptions are as supplied by the client and have not been verified by FIRA International who can take no responsibility for the accuracy of the description.*

**TEST REQUIREMENTS:**

Schedule 4 part II (based on BS 5852: 1979 Part 1)  
Schedule 5 part III (based on BS 5852: 1979 Part 1)

**RESULT:**

Pass - P0  
Pass - P1

FIRA International is a UKAS TESTING Laboratory No. 0174

Tests marked "Not UKAS Accredited" in this Report are not included in the UKAS Accreditation Schedule for our laboratory.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

Technical report references marked \* indicate this report is supplementary to the previous report with the same reference.

This Report relates to the sample(s) submitted for test and no others. Additions, deletions or alterations are not permitted.

Test reports are given to the client in confidence, and may only be reproduced in whole or in part with written permission from FIRA International Limited. Note that the words "**tested by FIRA International**" may be used in subsequent publicity for the product; "approved" must **not** be used.

Tests are carried out on the understanding that neither FIRA International Limited nor its officers can accept any legal responsibility for information or advice given or opinions expressed whether in response to specific enquiries or otherwise. This Report is given subject to the Terms of Business of FIRA International Limited which are available at <https://www.fira.co.uk/images/FIRA-International-Limited-Standard-Terms-of-Business-2018.pdf>

When a statement of conformity to a test standard is reported the test result(s) are unlikely to be the "true" result(s) due to measurement uncertainty. When the sample is tested under the criteria and conditions as defined in the method and the measured result is outside of the upper/lower acceptance limit and corrected for uncertainty at 95% probability, the risk of a false accept/reject is  $\leq 2.5\%$ . These results will be reported as Pass/Fail. If the test result(s) obtained under the same conditions is close to the upper/lower acceptance limit and could be either side of the accept/reject threshold these results will be reported as Fail"



0174

FL-61992-S2A\*  
Page 1 of 3

FIRA International  
Registered office: 3<sup>rd</sup> Floor Davidson  
Building, 5 Southampton Street, London,  
United Kingdom, WC2E 7HA.  
Registered in England No: 3181481

# TECHNICAL REPORT

## DESCRIPTION

Enquiry No: FL-61992-S2A\*

Item: One, Non-Visible Fabric – Ref: Black Loop Pile Velcrotex Velour 100% Sandstone Black Granite White Brown Batch 148-149

Supplied by: Allsave Textiles Ltd

*The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.*

## **FURNITURE AND FURNISHINGS (FIRE) (SAFETY) REGULATIONS 1988 - AMENDED 1989, 1993 AND 2010** **SCHEDULE 4 PART II FOR NON-VISIBLE COVERS- MODIFICATION TO BS 5852: PART I THE CIGARETTE TEST**

**Initial Inspection:** Condition as new

**Conditioning:** ≥3 days at indoor ambient conditions and ≥16 hours at 20±5°C & 50±20% rh

**Filling material:** A combustion modified high resilience foam 24-26kg/m<sup>3</sup> Ref: CMHR25.

**Test procedure:** As defined in Schedule 4 part II of the above Regulations

**Test conditions:** The test was conducted within the required conditions of 15-30°C & 20-70%rh

## RESULTS

| Source No. | Application No. | Smoke/ Smoulder | Result - Ignition/ Non-Ignition |
|------------|-----------------|-----------------|---------------------------------|
| 0          | 1               | 15min 48sec     | PASS N/I                        |
|            | 2               | 15min 57sec     | PASS N/I                        |

## COMMENTS

| SCHEDULE 4 PART II MODIFICATION TO BS 5852: PART 1 THE CIGARETTE TEST                                                                                                                         | APP.1         | APP.2         |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------|---------------|
| Both cigarettes were fully consumed within the stipulated 1 hour time period, however the cover and filling assembly continued to smoulder for greater than the stipulated 60min time period. | NO - PASS N/I | NO - PASS N/I |
| Progressive smouldering was established, the rate of smoulder was rapid, and the test was terminated before the stipulated time period                                                        | NO - PASS N/I | NO - PASS N/I |
| Flames occurred though progressive smouldering, therefore the test was terminated before the stipulated 60min time period as it was deemed unsafe to continue                                 | NO - PASS N/I | NO - PASS N/I |

## CONCLUSION

This non-visible fabric Ref: Black Loop Pile Velcrotex Velour 100% Sandstone Black Granite White Brown Batch 148-149, passes the test specified in Schedule 4 Part II of The Furniture and Furnishings (Fire) (Safety) Regulations 1988 - Amended 1989, 1993 and 2010.



# TECHNICAL REPORT

## DESCRIPTION

Enquiry No: FL-61992-S2A\*

Item: One, Non-Visible Fabric – Ref: Black Loop Pile Velcrotex Velour 100% Sandstone Black Granite White Brown Batch 148-149

Supplied by: Allsave Textiles Ltd

*The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.*

## **FURNITURE AND FURNISHINGS (FIRE) (SAFETY) REGULATIONS 1988 - AMENDED 1989, 1993 AND 2010** **SCHEDULE 5 PART III THE MATCH TEST (BASED ON BS 5852: 1979 PART 1)**

**Initial Inspection:** Condition as new

**Conditioning:** ≥3 days at indoor ambient conditions and ≥16 hours at 20±5°C & 50±20% rh

**Test procedure:** as defined in Schedule 5 part III of the above Regulations using specified combustion modified high resilience foam 24-26kg/m<sup>3</sup>.

**Test conditions:** The test was conducted within the required conditions of 15-30°C & 20-70%rh

## RESULTS

| Source No. | Application No. | Application Time | Flaming Time Following Removal of Source | Smoke/Smoulder | Result - Ignition/Non-Ignition |
|------------|-----------------|------------------|------------------------------------------|----------------|--------------------------------|
| 1          | 1               | 20sec            | 00min 01sec                              | 00min 10sec    | PASS N/I                       |
|            | 2               | 20sec            | 00min 01sec                              | 00min 09sec    | PASS N/I                       |

## COMMENTS

| SCHEDULE 5 PART III THE MATCH TEST BASED ON BS 5852: 1979 PART 1 THE MATCH TEST                                                                                                                                                                                                                           | APP.1         | APP.2         |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------|---------------|
| After removal of the ignition source the cover fabric melted open to expose the underlying filling material. The cover and filling assembly immediately ignited. The rate of fire development was rapid and the test was terminated before the stipulated 120sec time period as it was unsafe to continue | NO - PASS N/I | NO - PASS N/I |
| After removal of the ignition source the cover fabric melted open to expose the underlying filling material. The cover and filling assembly immediately ignited. Flames continued beyond the stipulated 120sec time period                                                                                | NO - PASS N/I | NO - PASS N/I |
| After removal of the ignition source the cover fabric ignited, flames spread across the surface of the cover, leaving behind an intact char. The cover continued to burn for greater than the stipulated 120sec time period                                                                               | NO - PASS N/I | NO - PASS N/I |
| After removal of the ignition source the cover ignited, the cover char split and the underlying filling material ignited, the cover and filling assembly continued to burn for greater than the stipulated 120sec time period                                                                             | NO - PASS N/I | NO - PASS N/I |
| All flames ceased within the permitted 120sec, the test assembly continued to smoulder for greater than the stipulated 15min time period                                                                                                                                                                  | NO - PASS N/I | NO - PASS N/I |

## CONCLUSION

This non-visible fabric sample Ref: Black Loop Pile Velcrotex Velour 100% Sandstone Black Granite White Brown Batch 148-149, passes the test specified in Schedule 5 Part III of The Furniture and Furnishings (Fire) (Safety) Regulations 1988 - Amended 1989, 1993 and 2010.

Approved by: Stephen Cotton  
Section Head - Flammability



\*\*\*\*\* End of Report \*\*\*\*\*



FL-61992-S2A\*  
Page 3 of 3

**firainternational**  
Proud to be part of 